

Technical Data Sheet

CE 300NW



Certificate No: 0338-CPD-392

300NW is a UV stabilized polypropylene needle punched non woven geotextile. It is manufactured at one of THRACE NWs&GEOs facilities that have achieved **ISO 9001:2000** certification for its systematic approach to quality. The construction of the geotextile makes **300NW** ideal for the following applications.

Applications and intended uses of the needle punched non woven geotextile



EN 13249	EN 13250	EN 13251	EN 13252	EN 13253	EN 13254	EN 13255	EN 13256	EN 13257	EN 13265
F	F	F	F	F	F	F		F	F
R	R	R	D	R	R	R		R	R
F+S	F+S	F+S	F+S	F+S	F+S	F+S		F+S	F+R
R+S	R+S	R+S	F+D	R+S	R+S	R+S		R+S	
F+R	F+R	F+R	F+S+D	F+R	F+R	F+R		F+R	
F+R+S	F+R+S	F+R+S		F+R+S	F+R+S	F+R+S		F+R+S	

It is resistant to commonly encountered soil chemicals, mildew and insects and is non biodegradable. **300NW** conforms to the property values listed below. Technical data are based on statistical analysis on 95% confidence limit.

PROPERTY	TEST METHOD	VALUE	METRIC UNITS	TOLERANCE	
MECHANICAL					
Tensile Strength (MD/CD)	EN 10319 / ASTM D4595	Average	kN/m	24.0/24.0	
Tensile Elongation (MD/CD)	EN 10319 / ASTM D4595	Average	%	65/65	
Grab Tensile Strength	ASTM D4632	Average	N	1500	
Trapezoidal Tear Strength	ASTM D4533	Average	N	430	
Puncture Strength	ASTM D4833	Average	N	780	
Mullen Burst	ASTM D3786	Average	kPa	2700	
Resistance to Static Puncture (CBR)	EN ISO 12236 / ASTM D6241	Average	N	4400	
Dynamic Perforation resistance	EN ISO 13433	Average	mm	13	
Pyramid Puncture resistance	EN 14574	Average	N	-	
HYDRAULIC					
Apparent Opening Size (AOS)	ASTM D4751	Average	µm	90	
Characteristic Opening Size (O ₉₀)	EN ISO 12956	Average	µm	80	
Water permittivity	EN11058 / ASTM D4491	Average	s ⁻¹	1.4	
Water permeability V _{IH50}	EN11058 / ASTM D4491	Average	m/sec*10 ⁻³	70	
Water flow rate	EN11058 / ASTM D4491	Average	l/m ² /sec	70	
Water Flow Capacity in the plane (MD/CD)	HG 1.0 at 20kPa	EN ISO 12958	Average	3.04/4.19	-
	HG 1.0 at 100kPa			1.64/2.34	-
	HG 1.0 at 200kPa			0.91/1.32	-
ENDURANCE					
Weathering Resistance	EN12224 / ASTM D4355	Average	%retain strength	90	
Resistance to Liquids – Acid & Alkaline	EN 14030	Average	%retain strength	90	
Oxidation & Soil Burial Resistance	EN13438 & EN12225	Average	%retain strength	90	
PHYSICAL					
Mass/Unit Area	EN 9864 / ASTM D5261	Average	gr/m ²	300	
Thickness (2kPa)	EN 9863-1 / ASTM D5199	Average	mm	2.0	
STANDARD PACKAGING					
Roll Width / Length	Typical	Typical	m	5.4/100	

NOTES:

- THRACE NWs&GEOs Technical Fabrics reserve the right to alter product specifications at any time without prior notice. It is the responsibility of all users to satisfy themselves that the above data are current.
- The geotextiles listed are CE marked and they come along with a CE certificate after a customer request.
- Polypropylene is the constituent polymer used in the production of the NW geotextiles series.
- To be covered within one month after installation. The above geotextile is predicted to be durable for more than 25 years in soil temperatures >25°C and are resistant to highly acid and alkaline environments on the basis of a durability assessment.
- F = Filtration, R = Reinforcement, S = Separation, D = Drainage

TÜV
AUSTRIA
HELLAS
ISO 9001:2008
Reg.No: 01010018

The information contained herein is furnished without charge or obligation and the recipient assumes all the responsibility for its use. Because conditions for use and handling may vary and are beyond our control, THRACE NWs&GEOs makes no representation about, and is no responsible or liable for, the accuracy or reliability of said information or performance of any product. Any specification, properties or applications listed herein are provided as information only in no way modify, amend, enlarge or create any warranty. Nothing contained herein is to be construed as permission or as any recommendation to infringe any patent.