

GlassPAR Net

TECHNICAL DATASHEET

		GlassPAR Net				
		75	110	165*	60 ADH.	U. o. M.
Weight	with resin	75	110	165	54	g/m ²
	only glass	61	85	135	44	
	adhesive	-	-	-	8	
Mesh size		5x5	10x10	4x4	2,9x2,9	mm
Composition	glass	82	82	82	68	%
	resin	18	18	18	19	
	adhesive	-	-	-	13	
	alkhali resistant resin	30	30	30	-	
	acr	70	70	70	100	
Glass filaments	MD	7	20	14	3	dtex
	CD	17	50	30	6,5	
Tensile strength at break	MD	900	1050	1950	500	N/5cm
	CD	750	1050	1800	550	
Elongation at break	MD/CD	3,6	3,6	3,6	4	%

*ETAG 004

SUPPLY CHARACTERISTICS

		GlassPAR Net				
		75	110	165	60 ADH.	U. o. M.
Width		100	100	110	5	cm
Length		50	50	50	90	m
Roll surface		50	50	55	4,5	m ²
Quantity per pallet		2100	1200	1650	n. a.	m ²
		54	30	30	864	n. of rolls
		n. a.	n. a.	n. a.	36	n. of boxes
Quantity per box		n. a.	n. a.	n. a.	24	n. of rolls

ed. January 2010