



GAVAZZI TESSUTI TECNICI S.p.A. s.u.

Sede centrale / Headquarter
Via Gavazzi, 3
23801 Calolziocorte (LC), Italia
Tel. +39 0341 641051 | Fax +39 0341 633004
info@gavazzispa.it | www.gavazzispa.it

COMPANY WITH
MANAGEMENT SYSTEM
CERTIFIED BY DNV
ISO 9001-ISO 50001

TECHNICAL SPECIFICATION		ARTICLE 0133-A	
ARTICLE DESCRIPTION			
THREADS SP 04/02/10 (UNI EN 1049-2)	Warp	16 ± 1 yarns / dm (leno)	
	Weft	9 ± 1 yarns / dm	
MESH WIDTH SP 04/02/11	Measured between yarn midpoints	approx. 12,5 x 11,5 mm	
WEIGHT SP 04/02/12 (ISO 3374)	Raw mesh	98 g/m ² ± 5%	
	Finished mesh	120 g/m ² ± 5%	
MAIN FEATURES			
MAIN APPLICATION (S)	Wall plaster reinforcement		
COMPOSITION	Fiberglass	approx. 82 %	
	Alkali resistant finish	approx. 18 %	
RESISTANCE TO TENSILE STRENGTH SP 04/02/13 (ISO 4606)	Warp	Breaking strength	Elongation
		Average value 1650 N/5 cm	5,0 % ± 1
	Weft	Average value 2000 N/5 cm	5,0 % ± 1
STANDARD PACKAGING			
Mesh width 1000 mm - roll length 50 m - on cardboard core and in polythene			
1 pallet of 110/130/120 cm contains 36 rolls i.e. 1800 m ²			
NOTES			
Specifications (SP) are the internal version of the national norms reported in brackets. The SP's differ from the norms for a few necessary modification of the procedures which do not influence the test results. A copy of the SP's is available on request.			
Above data are based on our experience. They are liable to amendments and should be verified by the customer in case of special uses. In order to verify that the technical data sheet in the hands of the customer is updated, its date should be reported on the order.			
UPDATED 07/01/2009		PLANT MNG. Signed on original copy	

