

TECHNICAL SPECIFICATION

ARTICLE V3-98-A

ARTICLE DESCRIPTION

7.07			
WEIGHT SP 04/02/12 rev. 02	raw mesh	78 g/m² ± 5%	
(ISO 3374)	finished mesh	98 g/m² ± 5%	
MESH WIDTH SP 04/02/11 rev. 01	measured between yarn midpoints	approx. 12,5 x 11,8 mm	

MAIN FEATURES

	COMPOSITION		Fiberglass	approx. 80 %	
			Alkali resistant finish	approx. 20 %	
RESISTANCE TO TENSILE STRENGTH SP 04/02/13 rev. 01 (ISO 4606)	V.		Breaking strength	Elongation	
	warp	Average value 1650 N/5 cm	4,5 % ± 1		
	weft	Average value 1400 N/5 cm	4,5 % ± 1		

STANDARD PACKAGING

Roll width 1000 mm - roll length 50 m - on cardboard core and in polythene

NOTES

Specifications (SP) are the internal version of the national norms reported in brackets. The SP's differ from the norms for a few necessary modification of the procedures which do not influence the test results. A copy of the SP's is available on request.

Above data are based on our experience. They are liable to amendments and should be verified by the customer in case of special uses. In order to verify that the technical data sheet in the hands of the customer is updated, its date should be reported on the order.

UPDATED 16/05/2005

PLANT MNG.



